

Masking Tape #140

Masking Tape 140micron x 48mm width x 30meter length



Features:

Color: Off-white
Specification: 48mm30m140U(mic)
Width: 48mm (± 1 mm)
Length: ≥ 30 m
Thickness: 142 microns (± 10 microns)
Initial Viscosity: ≥ 12
Stickiness (H): ≥ 4 hours
180° Peeling Strength: ≥ 6.5 N/25cm
Tensile Strength: ≥ 50 MPa
Elongation at Break: 10% \pm 2
Appearance: No stains, impurities, no fading

Standards:

GB/T 22378-2008 standard

Packing:

60pcs / Carton
05 rolls / Tower pack
12 packs / Carton

Carton Dimension:

45.1x34.0 x 25.5 cms

Carton Weight:

Gross Weight: 9.62kgs/carton
Net Weight: 9.52kgs/carton

Volume:

CBM 0.0391

Origin:

China



G132643002



GB/T 22378-2008 standard

Product Quality Inspection Report					
Order No.:	202402200048		Production Date:	2024/3/1	
Test Item	#307 Masking Tape		Colour	off-white	
specification	48mm* 30m * 140U(mic)		Report lot number	XSD-CP-202403-006	
No.	Test Item	Reference Standard	Test Value	Mode/Tool	Result
1	width (mm)	48mm±1mm	48	straightedge	qualified
2	length (m)	≥30m	30	GB/T30776-2014	qualified
3	thickness (um)	140U±10	142	GB/T7125-2014	qualified
4	initial viscosity#	≥12	15	GB/T4852-2002 (Rolling Sphere Method)	qualified
5	Stickiness (H)	≥4	>4	GB/T4851-2014	qualified
6	180°Peeling strength(N/25cm)	≥6.5	7.012	GB/T2792-1998	qualified
7	Tensile strength (Mpa)	≥50	100.439	GB/T7753-2014	qualified
8	Elongation at break (%)	10%±2	14.241	GB/2792-1998	qualified
9	Appearance	No stains, impurities, no fading	no impurities	GB/T30776-2014	qualified
Inspection condition and decision	Temperature: 23°C±1°C		湿度：50%+5%		
	Sample source：	Bulk sampling	Comprehensive Assessment:	qualified	
	Inspector: Liao Shuilian		Test date:	2024/3/15	
Our products are inspected according to GB/T 22378-2008 standard.					
This inspection report is the test value of our company in the laboratory environment, and the report is only responsible for the sample or sampling analysis results of this time.					